

Features

- High temperature and M.V.T. rate
- Strong physical properties
- Tin free
- Hydrolysis resistance

Physical Properties

*Properties	Method	Unit	**Value	Note
Thickness		mm	0.015	
Width		mm inch	1524 60	
Color			Translucent	
M.V.T.	ASTM E96-93BW 23°C/50%R.H.	g/m ² x24hrs	12000	
M.V.T.	JIS L1099-1993 A-1(CaCl ₂)40 °C 90% R.H.	g/m ² x24hrs	3100	
W.P.R.	JIS L1092-1998 B Method	mmH ₂ O	Over 10000	
Film Melting Point		°C	175	
Specific Gravity	ASTM D792		1.20	
Elongation	ASTM D882	%	487	
PE Carrier			Yes	

**Actual results may yield up to ±15%.

*Data provided are used solely for references only, and are not guaranteed statements.