

DINTEX® LW 5-6

Features

- Excellent M.V.T.
- Great hydrolysis resistance
- Easy for lamination
- Stable W.P.R.
- Remarkable physical properties

Physical Properties

Properties	Method	Unit	Value	Note
Thickness		mm	0.020	
Width		mm inch	1524 60	
M.V.T.	ASTM E96-93BW 23°C/50%R.H.	g/m ² x24hrs	10000	
M.V.T.	JIS L1099-1993 A-1 (CaCl ₂)40°C 90%R.H.	g/m ² x24hrs	4100	
W.P.R.	JIS L1092-1998 B Method	mmH ₂ O	Over 10000	
Specific Gravity	ASTM D792		1.28	
Hardness	ASTM D2240	Shore A	85	
Elongation	ASTM D882	%	376	

** Data provided are used solely for reference only, and are not guaranteed statements. Actual results may vary.



DING ZING CHEMICAL PRODUCTS CO., LTD.

SINCE 1981

http://www.dingzing.com e-mail: film@dingzing.com.tw Tel: +886 - 7 - 8070166
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616