

Ding Zing® Film FS2293

Features

- Polyurethane polyester base
- Good barrier to liquid
- Good oil resistance
- High elongation at break
- High heat resistance
- High tensile strength
- Good tear resistance
- Excellent flexibility at low temperature

Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		86 ±3	
Specific Gravity		ASTM D792		1.19	
Tensile Strength	Kg/cm ²	ASTM D412	MD	623	
			CD	617	
Elongation	%	ASTM D412	MD	523	
			CD	529	
300% Modulus	Kg/cm ²	ASTM D412	MD	203	
			CD	162	
Tear Strength	Kg/cm	ASTM D624	MD	130	
			CD	130	
Film Melting Point	°C			144	
UV stability	Grade	ASTM D1148		1	

**Actual results may yield up to ±15%.

*Data provided are used solely for references only, and are not guaranteed statements.



DING ZING CHEMICAL PRODUCTS CO., LTD.

SINCE 1981

http://www.dingzing.com e-mail: film@dingzing.com.tw Tel: +886 - 7 - 8070166
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616