

Ding Zing® Film FT585S

Features

- Polyurethane polyether base
- Superior hydrolysis resistance
- Softness maintained at low temperature
- Matte finish
- Smooth with soft touch
- Resistance to aging

Physical Properties

| *Properties | Unit | Method | Direction | **Value | Note |
|--------------------|--------------------|---|-----------|------------|------|
| Hardness | Shore A | ASTM D2240 | | 87±3 | |
| Specific Gravity | | ASTM D792 | | 1.13 | |
| Tensile Strength | Kg/cm ² | ASTM D412 | MD CD | 335 330 | |
| 300% Modulus | Kg/cm ² | ASTM D412 | MD CD | 100 95 | |
| Elongation | % | ASTM D412 | MD CD | 570 605 | |
| Tear Strength | Kg/cm | ASTM D624 (Die C) | MD CD | 125 125 | |
| Film Melting Point | °C | | | 140 | |
| QUV Discoloration | Grade | ASTM G154 (45°C/24hrs/0.78W/m ²) | | 3 | |

**Actual results may yield up to ±15%.

*Data provided are used solely for references only, and are not guaranteed statements.



DING ZING CHEMICAL PRODUCTS CO., LTD.

SINCE 1981

http://www.dingzing.com e-mail: film@dingzing.com.tw Tel: +886 - 7 - 8070166
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616