

## Ding Zing® Film FS8080

### Features

- Polyurethane polyester base
- No plasticizer
- Good UV stability
- Easy for high frequency welding
- Transparent with smooth surface

### Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		80±3	
Specific Gravity		ASTM D792		1.21	
Tensile Strength	Kg/cm <sup>2</sup>	ASTM D412	MD CD	172 161	
300% Modulus	Kg/cm <sup>2</sup>	ASTM D412	MD CD	56 55	
Elongation	%	ASTM D412	MD CD	806 846	
Tear Strength	Kg/cm	ASTM D624 (Die C)	MD CD	71 73	
Film Melting Point	°C			100	
QUV Discoloration	Grade	ASTM G154 (45°C/24hrs/0.78W/m <sup>2</sup> )		4	

\*\*Actual results may yield up to ±15%.

\*Data provided are used solely for references only, and are not guaranteed statements.



**DING ZING CHEMICAL PRODUCTS CO., LTD.**

SINCE 1981

<http://www.dingzing.com> e-mail: [film@dingzing.com.tw](mailto:film@dingzing.com.tw) Tel: +886 - 7 - 8070166  
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616