

## Ding Zing® Film FT3070

### Features

- Polyurethane polyether base
- Good hydrolysis resistance
- Excellent softness
- Very good low temperature flexibility

### Physical Properties

*Properties	Unit	Method	Direction	**Value	Note
Hardness	Shore A	ASTM D2240		70±3	
Specific Gravity		ASTM D792		1.07	
Tensile Strength	Kg/cm <sup>2</sup>	ASTM D412	MD	320	
			CD	272	
Elongation	%	ASTM D412	MD	655	
			CD	802	
300% Modulus	Kg/cm <sup>2</sup>	ASTM D412	MD	70	
			CD	46	
Tear Strength	Kg/cm	ASTM D624	MD	90	
			CD	92	
Film Melting Point	°C			140	
UV stability	Grade	D1148		4	

\*\*Actual results may yield up to ±15%.

\*Data provided are used solely for references only, and are not guaranteed statements.



**DING ZING CHEMICAL PRODUCTS CO., LTD.**

SINCE 1981

<http://www.dingzing.com> e-mail: [film@dingzing.com.tw](mailto:film@dingzing.com.tw) Tel: +886 - 7 - 8070166  
No.8-1, Pei-Lin Rd. Hsiao-Kang Dist., Kaohsiung, Taiwan Fax: +886 - 7 - 8071616