

# DING ZING Specification Sheet

## 熱熔膠

FS5723X1+DZ03  
(0.254mm/10mil)

- 聚胺酯薄膜(TPU)
- 可低溫加工(75°C)
- 真皮,PU皮,超細纖維接著
- 適用3C產品包材
- 適合多種貼合
- 環保材質

物性	單位	試驗方法	試驗結果
硬度 Hardness	Shore A/D	ASTM D2240	97/40
比重 Specific Gravity	—	ASTM D792	1.19
抗張強度 Tensile Strength	kg/cm <sup>2</sup>	ASTM D412	warp: 313 weft: 333
300%模數 300 % Modulus	kg/cm <sup>2</sup>	ASTM D412	warp: 57 weft: 54
伸長率 Ultimate Elongation	%	ASTM D412	warp: 923 weft: 963
撕裂強度 Tear Strength	kg/cm	ASTM D624(Die C)	warp: 86 weft: 80
薄膜熔點 Film Melting Point	°C		57



**DING ZING CHEMICAL PRODUCTS**

SINCE 1981

No. 8-1, Pei-Lin Rd., Hsiao-Kang Dist., Kaohsiung Taiwan, +886-7-8070166,  
www.dingzing.com